

FEROLITE NAM 39 NON ASBESTOS GASKET JOINTING SHEET



Applications:

Water/Oil resistant gasket material for light to medium loading. Suitable for low operating pressure, e.g. transformers, compressors and also used for easily deformable components with low surface pressure like valve covers and pans in internal combustion engines.

General data:

Material Composition (Type of fibres) Cellulose Fibre, Mineral Fibre & Organic Fibre.

Binders NBR

OPERATING CONDITION

Max.Peak Temp 250°C

Max. Continuous Temp 180°C

Max.Continuous Temp.with steam 120°C

Max. Operating Pressure 50 Kg/cm²

Physical Properties:

The following Information applies to material thickness 2.0 mm.

S.NO.	PROERTIES	TEST METHOD	UNIT	SPECIFIED VALUE
1.	DENSITY		gm/cm ³	1.70 - 2.00
2.	TENSILE STRENGTH			
	(a) ACC to ASTM F152(ACROSS GRAIN)		N/mm ²	> 7
	(b) ACC to DIN52910 (ACROSS GRAIN)		N/mm ²	> 5
3.	COMPRESSIBILITY	ASTM F36A	%	5 – 15
4.	RECOVERY	ASTM F36A	%	> 40
5.	FLUID ABSORPTION	ASTM F 146		
	(a) IN ASTM OIL NO. 3			
	INCREASE IN MASS		%	< 15
	INCREASE IN THICKNESS		%	< 10
	(b) IN FUEL B	ASTM F 146		
	INCREASE IN MASS		%	< 10
	INCREASE IN THICKNESS		%	< 10
	(c) IN WATER/ANTIFREEZE	ASTM F 146		
	INCREASE IN MASS		%	< 15
	INCREASE IN THICKNESS		%	< 15
6.	IGNITION LOSS	DIN 52911	%	< 40
7.	SEALABILITY AGAINST Nitrogen	DIN 3535	cm ³ /min.	-
8.	STRESS RESISTANCE			
	16h 300°C	DIN 52913	N/mm ²	–
	16h 175°C	DIN 52913	N/mm ²	–

FEROLITE NAM 39

